

## VISCOSE NONWOVEN S-CV 40

### ► Technical Specifications

|   |                            |                |
|---|----------------------------|----------------|
| <b>Fiber composition</b>                                      | 100 % viscose, with binder |                |
| <b>Bonding</b>  | Chemical                   |                |
| <b>Weight [g/m<sup>2</sup>]</b>                               | 40                         | DIN EN 29073-1 |
| <b>Thickness [mm]</b>   | 0,33                       | DIN EN 29073-2 |
| <b>Maximum tensile strength<br/>machine direction [N/5cm]</b> | 96                         | DIN EN 29073-3 |
| <b>Maximum tensile strength<br/>cross direction [N/5cm]</b>   | 11                         | DIN EN 29073-3 |
| <b>Maximum tensile elongation<br/>machine direction [%]</b>   | 6                          | DIN EN 29073-3 |
| <b>Maximum tensile elongation<br/>cross direction [%]</b>     | 34                         | DIN EN 29073-3 |
| <b>Size of pores largest/many [µm]</b>                        | 119/59                     |                |
| <b>Air permeability [l/m<sup>2</sup>/s]</b>                   | 4420                       | EN ISO 9237    |

All data provided are average values.

The technical characteristics are subjects to the usual fluctuations and are therefore not binding.